

CONVERSION FACTORS

10K to Alloy Wt. x .77	PT to 14K Wt. x .57
10K to SS Wt. x .88	PT to 18K Wt. x .70
10K to 14K Wt. x 1.14	SS to Alloy Wt. x .88
10K to 18K Wt. x 1.30	SS to 10K Wt. x 1.14
14K to Alloy Wt. x .67	SS to 14K Wt. x 1.30
14K to SS Wt. x .77	SS to 18K Wt. x 1.48
14K to 10K Wt. x .88	Alloy to SS Wt. x 1.14
14K to 18K Wt. x 1.14	Alloy to 10K Wt. x 1.30
14K to PT Wt. x 1.75	Alloy to 14K Wt. x 1.48
18K to 10K Wt. x .77	Alloy to 18K Wt. x 1.69
18K to 14K Wt. x .88	Wax to Brass Wt. x 8.50
18K to PT Wt. x 1.42	Wax to 14K Wt. x 14.00

WEIGHTS AND MEASURES

<i>To Change From</i>	<i>To</i>	<i>Multiply By</i>
KARATS	PENNYWEIGHT (DWT)	0.1286
KARATS	GRAMS	0.2
GRAMS	KARATS	5
GRAMS	PENNYWEIGHT	0.64301
GRAMS	KILOGRAMS	0.001
GRAMS	OUNCES, AVOIR	0.03527
GRAMS	OUNCES, TROY	0.03215
GRAMS	POUNDS, AVOIR	0.0022
GRAMS	POUNDS, TROY	0.00268
INCHES	MILLIMETERS	25.4
KILOGRAMS	GRAMS	1,000
KILOGRAMS	OUNCES, AVOIR	35.274
KILOGRAMS	OUNCES, TROY	32.1507
KILOGRAMS	PENNYWEIGHT (DWT)	643.014
KILOGRAMS	POUNDS, AVOIR	2.2046
KILOGRAMS	POUNDS, TROY	2.6792
MILLIMETERS	INCHES	0.03937
OUNCES, AVOIR	GRAMS	28.3495
OUNCES, AVOIR	KILOGRAMS	0.02835
OUNCES, AVOIR	OUNCES, TROY	0.91146
OUNCES, AVOIR	PENNEYWEIGHT (DWT)	18.2291
OUNCES, AVOIR	POUNDS, AVOIR	0.0625
OUNCES, AVOIR	POUNDS, TROY	0.076
OUNCES, TROY	GRAMS	31.1035
OUNCES, TROY	KILOGRAMS	0.031103
OUNCES, TROY	OUNCES, AVOIR	1.0971
OUNCES, TROY	PENNEYWEIGHT (DWT)	20
OUNCES, TROY	POUNDS, AVOIR	0.0686
OUNCES, TROY	POUNDS, TROY	0.08333
PENNEYWEIGHT (DWT)	KARATS	7.778
PENNEYWEIGHT (DWT)	GRAMS	1.5552
PENNEYWEIGHT (DWT)	KILOGRAMS	0.001555
PENNEYWEIGHT (DWT)	OUNCES, AVOIR	0.05486
PENNEYWEIGHT (DWT)	OUNCES, TROY	0.05